

DIXIE
Gun Works, Inc.

ORDER TOLL FREE
800-238-6785



BLACK POWDER GUNS

ANTIQUÉ GUN PARTS

SHOOTING SUPPLIES

ARTILLERY RELEASE FORM

Please print this document using your browser's "PRINT" button or select print from the file menu. Fill out the form and mail, email or fax it along with your cannon order to Dixie Gun Works. If you have any questions please contact us at info@dixiegunworks.com or call 731-885-0561.

NOTICE: READ, SIGN AND SEND WITH YOUR ORDER!

When ordering any of our $\frac{1}{4}$, $\frac{1}{2}$, $\frac{2}{3}$, $\frac{3}{4}$ or full scale cannons, the customer is required to sign a form of necessary safety rules and powder loads. Please make a copy of the form (below), sign it and return it with your order. You must return a signed copy of the form before your order can be shipped. This form is necessary for cannons with carriages or barrels only.

BASIC SAFETY REGULATIONS FOR SHOOTING MUZZLELOADING ARTILLERY

A portion of the following regulations was taken from "Safety Rules and Procedures for Shooting Muzzleloading Artillery" compiled by The Artilleryman magazine. You may send for the pamphlet free of charge from The Artilleryman, 520 Folly Road, Suite 25 PMB 379, Charleston, SC 29412.

1. Powder Charge Preparations: Black powder (**ONLY**) should not exceed 2 oz. Fg per any 2 $\frac{1}{4}$ " bore diameter.
2. Pre-measured powder charges should be wrapped in heavy duty aluminum foil, double thickness.
3. All crew members should wear ear protection devices.
4. No one should cross in front of the muzzle at any time during the cleaning, loading or firing procedure.
5. The ammunition box shall be attended at all times, or be locked. The interior shall be lined with a non-sparking material and the box itself shall be stoutly constructed of wood or metal.
6. No smoking at any time on the line.
7. No drinking alcoholic beverages on the line.
8. Projectiles shall be constructed so that they easily pass through a sizing gauge with finger or thumb pressure only. The sizing gauge to be a length at least 1.5 times the length of the projectile and an inside diameter no greater than bore diameter when the tube was new.

9. It is necessary to swab the bore with a wet mop between shots. ALWAYS ALLOW 15 MINUTES TO ELAPSE BETWEEN FIRING AND RELOADING THE NEXT POWDER CHARGE.

Signature of Purchaser

Date

Complete Address

- Print this document and keep the bottom page for your records. You **MUST** sign and return the first two pages as indicated below:

Mail to: Dixie Gun Works
P.O. Box 130
Union City, TN 38281

Email to: info@dixiegunworks.com

Fax to: 731-885-0440

DIXIE
Gun Works, Inc.

ORDER TOLL FREE
800-238-6785



BLACK POWDER GUNS

ANTIQUÉ GUN PARTS

SHOOTING SUPPLIES

BASIC SAFETY REGULATIONS FOR SHOOTING MUZZLELOADING ARTILLERY

A portion of the following regulations was taken from "Safety Rules and Procedures for Shooting Muzzleloading Artillery" compiled by The Artilleryman magazine. You may send for the pamphlet free of charge from The Artilleryman, 520 Folly Road, Suite 25 PMB 379, Charleston, SC 29412.

1. Powder Charge Preparations: Black powder (ONLY) should not exceed 2 oz. Fg per any 2 ¼" bore diameter.
2. Pre-measured powder charges should be wrapped in heavy duty aluminum foil, double thickness.
3. All crew members should wear ear protection devices.
4. No one should cross in front of the muzzle at any time during the cleaning, loading or firing procedure.
5. The ammunition box shall be attended at all times, or be locked. The interior shall be lined with a non-sparking material and the box itself shall be stoutly constructed of wood or metal.
6. No smoking at any time on the line.
7. No drinking alcoholic beverages on the line.
8. Projectiles shall be constructed so that they easily pass through a sizing gauge with finger or thumb pressure only. The sizing gauge to be a length at least 1.5 times the length of the projectile and an inside diameter no greater than bore diameter when the tube was new.
9. It is necessary to swab the bore with a wet mop between shots. **ALWAYS ALLOW 15 MINUTES TO ELAPSE BETWEEN FIRING AND RELOADING THE NEXT POWDER CHARGE.**

